

FEDRIGONI

PAPER

FREELIFE MÉRIDA

High quality papers and boards, pulp-coloured, with 40% recycled material certify FSC® and 55% pure environmentally friendly fiber certify FSC® and 5% of cotton fiber. Felt marked on both side. Available in nine colours.

DESCRIPTION

SIZE	SIZE	SUBSTANCE
70X100	LG	100 140 215 280 320

RANGE

SUBSTANCE	VSA	TABER STIFFNESS		TENSILE STRENGTH	
		long ± 10%	cross ± 10%	long ± 10%	cross ± 10%
ISO 536	ISO 534	ISO 2493		ISO 1924	
g/m ²	cm ³ /g	mN		kN/m	
100 ± 3%	1,43	30	18	7	3,2
140 ± 3%	1,43	60	28	9,1	4,2
215 ± 4%	1,43	100	45	11,7	6
280 ± 5%	1,43	200	100	12,9	7,2
320 ± 5%	1,43	350	170	-	-

TECHNICAL FEATURES

ref. standard/instrument
unit of measure

Brightness (col. White) -
ISO 2470 (R457) - 89% ± 2
Relative Humidity 50% ±
5 ref. TAPPI 502-98



ECOLOGICAL FEATURES

Given the considerable amount of recycled content within the product it is normal for there to be a slight variation in the shade from one making to the next, and occasional small residues from the recycling process. The product is completely biodegradable and recyclable. Special runs available upon request.

NOTES

FREELIFE MÉRIDA

Freelife Mérida papers and boards are ideal for any kind of publishing, packaging and commercial printing. They are held in high regard for packaging, shopper, editions, brochures, booklets and coordinated graphic materials.

APPLICATIONS

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. Due to the characteristic felt marking, the paper requires specific printing pressure settings.

PRINTING SUGGESTIONS

Varnishing and plastic laminating must be assessed in advance. The varnish coated with an offset machine is almost fully absorbed and therefore does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of felt-marked papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

CONVERTING SUGGESTIONS

