

SIRIO WHITE WHITE

Uncoated papers and boards, certify FSC®, made with ECF (Elemental Chlorine Free) pulp. Extra white and high strength. Substances over 200 gsm are wet laminated in the paper machine except for the 700 gsm because it's off-machine laminated.

DESCRIPTION

SIZE	GRAIN	SUBSTANCE
71X101	LG	90 130 170 200 240 280 350 400 700

RANGE

SUBSTANCE	VSA	ROUGHNESS	TABER STIFFNESS 15°		TENSILE STRENGTH	
ISO 536	ISO 534	ISO 8791-2	ISO 2493		ISO 1924	
g/m²	cm³/g	mN	kN/m			
			long ± 10%	cross ± 10%	long ± 10%	cross ± 10%
90 ± 3%	1,27	350 ± 50	6,5	3	5,2	3,2
130 ± 3%	1,27	350 ± 50	27	12	8,5	4,5
170 ± 3%	1,27	300 ± 50	50	25	10,4	5,2
200 ± 4%	1,27	300 ± 50	80	37	11,1	6,5
240 ± 5%	1,27	250 ± 50	120	50	13	7,8
280 ± 5%	1,27	250 ± 50	210	90	19,6	9,1
350 ± 5%	1,25	250 ± 70	370	165	-	-
400 ± 5%	1,25	250 ± 70	480	230	-	-
700 ± 5%	1,15	750 ± 100	1800	900	-	-

TECHNICAL DESCRIPTION

ref. standard/instrument
unit of measure

Brightness - ISO 2470
(R457) - 112% ± 2 Opacity
- ISO 2471 (90 g/m2) 92% ± 2
Relative Humidity 50% ± 5 ref. TAPPI 502-98



Aticelca® 10788-0009

ECOLOGICAL FEATURES

The product is recyclable according to Aticelca 501:2025 and Cepi V.2-2022, based on UNI 11743:2019.

NOTES

Manufactured in our mills with certified biomethane replacing natural gas and with electricity from renewable sources.

Special runs available upon request.

SIRIO WHITE WHITE

Sirio White-White is ideal for packaging, coordinated graphic materials, covers, inserts, de luxe brochures. Best performances are found when extra white and highly strength mechanical features are required.

DESCRIPTION

Can be used without problems with the main printing systems: letterpress, offset, blind embossing, hot foil stamping, thermography and screen printing. The macro-porous surface suggests the use of oxidative drying inks. In case of huge ink coverage we recommend to set to the minimum the ink load in order to let the ink drying properly.

PRINTING SUGGESTIONS

Varnishing and plastic laminating must be assessed in advance. The varnish coated with an offset machine is almost fully absorbed and therefore it does not improve gloss or protection. Screen-printing varnishing achieves better results, although it is often necessary to perform two shots to achieve a distinctly evident result. The surface roughness typical of uncoated papers may give rise to micro defects with plastic laminating caused by incomplete adhesion of the film to the substrate. Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing.

CONVERTING SUGGESTIONS

