

SYMBOL TATAMI

Environmentally-friendly ECF papers and boards of high thickness, certify FSC®. Coated on both sides with Matt finish. Available in white or slightly lvory colours.

DESCRIPTION

RANGE

SIZE	GRAIN	SUBSTANCE
64X88	LG	115 135 150 170 200 250
70X100	LG	115 135 150 170 200 250

VSA	OPACITY	ROUGHNESS	TENSILE STRENGTH ISO 1924	
ISO 534	ISO 2471	ISO 8791-2		
cm³/g	%	ml/min	kN/m	
			long ± 10%	cross±10%
1,27	95±2	55 ± 20	6,8	4,7
1,27	96±2	55 ± 20	8,2	5,7
1,27	97±2	55 ± 20	9,6	6,6
1,3	-	55 ± 20	10,8	7,5
1,3	-	55 ± 20	11	7,8
1,3	-	55 ± 20	-	-
	ISO 534 cm³/g 1,27 1,27 1,27 1,27 1,3 1,3	ISO 534 ISO 2471 cm³/g % 1,27 95±2 1,27 96±2 1,27 97±2 1,3 - 1,3 -	ISO 534 ISO 2471 ISO 8791-2 cm³/g % ml/min 1,27 95±2 55±20 1,27 96±2 55±20 1,27 97±2 55±20 1,3 - 55±20 1,3 - 55±20	$\begin{array}{c ccccccccccccccccccccccccccccccccccc$

TECHNICAL FEATURES

Ref. standard/instrument unit of measure

Brightness (col. White) ISO 2470 (R457) - 97% ± 2 Brightness (col. lvory) ISO 2470 (R457) - 85% ± 2 Relative humidity $50\% \pm 5$ ref. TAPPI 502-98





LIFE

The product is completely bio-degradable and recyclable. Special runs available upon request.

ECOLOGICAL FEATURES

NOTES

UNI EN ISO 9001:2015 - CQ 539 UNI EN ISO 14001:2015 - CQ 7847 UNI EN ISO 45001:2018 - CQ 26471 PRODUCT DATA SHEET SYM/459 Update 09/2015 Rev. nº 07

SYMBOL TATAMI

Symbol Tatami has been created for standard uses, from booklets to the boxes. The high bulk and the thickness give high consistency, which is widely used in order to give prestige to many graphic-publishing products. The good opacity ensures an excellent verso/recto printing performance, also with the lower substances. Thanks to the high Stiffness, the substance 250 gsm is especially suitable for converting uses.

Can be used with the main printing systems: letterpress, offset, blind embossing, hotfoil stamping, thermographic and screen printing. In offset printing we suggest to use oxidative drying inks.

Good results with major processing operations such as: cutting, die-cutting, scoring, folding and glueing, varnishing and plastic laminating. We suggest to scoring all the substances above 150 gsm.

, scoring, CONVERTING

APPLICATIONS

PRINTING

SUGGESTIONS

