

## **ICE-PROOF BRUT DE VÉLIN WS**

Wet-strength uncoated felt-marked paper for labels, anti-mould, acid-free and ice-bucket Roof thanks to a patented process (treatment in the mass). The paper is made from pure E.C.F. cellulose pulp, FSC® certified. Available in Alaska shade.

DESCRIPTION

SIZE	GRAIN	SUBSTANCE
72X102	LG	95

SUBSTANCE	BULK	OPACITY		COBB 60	W.B.R.	DRY TENSILE STRENGTH	
ISO 536	ISO 534	ISO 2471		ISO 535	ISO 3781	ISO 1924	,
g/m²	cm³/g	%		g/m²	%	kN/m	
		DRY	WET			long±10%	trasv±10%
95 ± 3%	1,28	93 ± 2	≥89	25 ± 4	≥12	6,5	3

## TECHNICAL FEATURES

ref. standard/instrument unit of measure

Brightness (col. Alaska) ISO 2470 - 101% ± 2

CIE Whiteness (col. Alaska) 123% ± 4

Relative Humidity 50% ± 5 ref. TAPPI 502-98

Roughness Bendtsen (ISO 8791-2) Top. 500 ± 100 ml/min.













ECOLOGICAL FEATURES


Special runs available upon request.

NOTES

## **ICE-PROOF BRUT DE VÉLIN WS**

For labelling, always observe the correct indications as regards grain direction. It must be parallel to the base of the bottle (see drawings).

**APPLICATIONS** 



Suitable with the main printing systems: offset, blind embossing, hot foil stamping, thermography, screen printing and flexography. With offset printing, it's recommend the use of UV or H-UV drying inks.

PRINTING SUGGESTIONS

The varnish printed with an offset machine is almost fully absorbed and therefore it doesn't improve gloss or protection. Good results with major processing operations such as: cutting, die-cutting and glueing.

CONVERTING SUGGESTIONS

