

## **SATIN WS**

Wet-strength uncoated smooth paper for labels with Satin finish, made from pure E.C.F. Ellulose pulp, FSC® certified. The smooth feel is the result of a soft-calendaring. Available in 2 shades: Classic White and Soft Ivory.

**DESCRIPTION** 

SIZE	GRAIN	SUBSTANCE
72X102	LG	80

SUBSTANCE	BULK	OPACITY		COBB 60	W.B.R.	DRY TENSILE STRENGTH*	
ISO 536	ISO 534	ISO 2471		ISO 535	ISO 3781	ISO 1924	,
g/m²	cm³/g	%		g/m²	%	kN/m	
		DRY	WET			long±10%	trasv±10%
80 ± 3%	1,1	88±2	≥76	25 ± 4	≥11	7,2	3,5

## TECHNICAL FEATURES

ref. standard/instrument unit of measure

Brightness (Classic White) ISO 2470 - 100% ± 2

CIE Whiteness (Classic White) 142% ± 4

Brightness (Soft Ivory) ISO 2470 - 67% ± 2

Relative Humidity  $50\% \pm 5$  ref. TAPPI 502-98

Roughness Bendtsen (ISO 8791-2)\* Top.  $110 \pm 100$  ml/min.







Special runs available upon request.

SPECIFIC TREATMENTS

ECOLOGICAL FEATURES


NOTES

<sup>\*</sup> Before the embossed

## **SATIN WS**

For labelling, always observe the correct indications as regards grain direction. It must be parallel to the base of the bottle (see drawings).

**APPLICATIONS** 



Suitable with the main printing systems: offset, blind embossing, hot foil stamping, thermography and screen printing. The macroporous surface requires the use of oxidative drying inks.

PRINTING SUGGESTIONS

The varnish printed with an offset machine is almost fully absorbed and therefore it doesn't improve gloss or protection. Good results with major processing operations such as: cutting, die-cutting and glueing.

CONVERTING SUGGESTIONS

