

SÉRAC WS

Wet-strength uncoated rough paper for labels, acid-free, anti-mould, made from pure E.C.F. cellulose pulp, FSC® certified. Available in Ice White shade.

DESCRIPTION

SIZE	GRAIN	SUBSTANCE
72X102	LG	90

RANGE

SUBSTANCE	BULK	OPACITY		COBB 60	W.B.R.	DRY TENSILE STRENGTH*	
ISO 536	ISO 534	ISO 2471		ISO 535	ISO 3781	ISO 1924	
g/m²	cm³/g	%		g/m²	%	kN/m	
		DRY	WET			long±10%	trasv±10%
90 ± 3%	1,4	94 ± 2	≥ 80	25 ± 4	≥ 11	7,0	3,5

TECHNICAL
FEATURES

ref. standard/instrument
unit of measure

Brightness (Classic White)
ISO 2470 - 100% ± 2

CIE Whiteness (Classic White)
154% ± 4

Relative Humidity 50% ± 5
ref. TAPPI 502-98

Roughness Bendtsen (ISO 8791-2)*
Top. 7500 ± 200 ml/min.

* Before the embossed



SPECIFIC
TREATMENTS



ECOLOGICAL
FEATURES


Special runs available upon request.

NOTES

SÉRAC WS

For labelling, always observe the correct indications as regards grain direction. It must be parallel to the base of the bottle (see drawings).

APPLICATIONS



Suitable with the main printing systems: offset, blind embossing, hot foil stamping, thermography and screen printing. The macroporous surface requires the use of oxidative drying inks.

PRINTING SUGGESTIONS

The varnish printed with an offset machine is almost fully absorbed and therefore it doesn't improve gloss or protection. Good results with major processing operations such as: cutting, die-cutting and glueing.

CONVERTING SUGGESTIONS